

This Page Is Inserted by IFW Operations
and is not a part of the Official Record

BEST AVAILABLE IMAGES


Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

**As rescanning documents *will not* correct images,
please do not report the images to the
Image Problem Mailbox.**



(18)



Europäisches Patentamt
European Patent Office
Office européen des brevets

(11) Publication number:

0 151 346
A1

(12)

EUROPEAN PATENT APPLICATION

(21) Application number: 84308760.2

(51) Int. Cl.⁴: **C 03 C 3/089**
C 03 C 3/091, C 03 C 4/08

(22) Date of filing: 14.12.84

(30) Priority: 13.01.84 FR 8400481

(43) Date of publication of application:
14.08.85 Bulletin 85/33

(84) Designated Contracting States:
BE DE GB IT NL

(71) Applicant: Corning Glass Works
Houghton Park
Corning New York 14831(US)

(72) Inventor: Boudot, Jean Emile
2 Rue Du Haut Changis
Tour Beau-Site Avon(FR)

(72) Inventor: Mazeau, Jean-Pierre
50 Voie De La Liberté
Samoreau Avon(FR)

(74) Representative: Smith, Sydney et al,
High Holborn House 52/54 High Holborn
London WC1V 6SH(GB)

(54) Glasses for ophthalmic applications.

(57) This invention is concerned with the production of glasses suitable for ophthalmic applications having refractive indices of 1.523 ± 0.004 , Abbe number between 51-59, densities less than 2.43g/cm^3 , transmissions at 400nm in 2 mm thickness greater than 89%, and a UV cutoff between 310-335nm, said glasses consisting essentially, in weight percent on the oxide basis, of:

SiO ₂	49-71	Li ₂ O + Na ₂ O + K ₂ O	8-20
B ₂ O ₃	5-26	TiO ₂	1.8-6
Al ₂ O ₃	0-14	ZrO ₂	0-5.5
Li ₂ O	0-4	As ₂ O ₃ and/or Sb ₂ O ₃	0-0.7
Na ₂ O	0-16	Cl and/or Br	0-1
K ₂ O	0-20	CaO and/or MgO	0-4
		and/or ZnO and/or BaO	

EP 0 151 346 A1

- 1 -

GLASSES FOR OPHTHALMIC APPLICATIONS

The present invention relates to glasses for ophthalmic applications which, in addition to the properties of ultraviolet radiation (UV) absorption and high transmission in the visible (absence of coloration), have a low density, as well as corrective lenses produced from these glasses.

These glasses are characterized by an index of refraction (n_d) of 1.523 ± 0.004 , an Abbe number (V_d) between 51-59, and a density (D) less than 2.43g/cm^3 . Their transmission at 400nm is, for a thickness of 2mm, greater than 89%. Their UV cutoff, defined as the wavelength for which the transmission is equal to 1% for a thickness of 2mm, is between 310-335nm. Moreover, they exhibit excellent chemical durability (A.O. test).

Lenses of inorganic glass ("white" or tinted) for ophthalmic use have, to a very great extent, an index of refraction $n_d = 1.523$. The "white" (or tinted) glasses used at the present time and which exhibit in certain cases a UV cutoff higher than 300nm, have a density at least equal to 2.54g/cm^3 . A reduction of the density and, consequently, of the weight of the lens, offers an obvious advantage for the wearer and

that regardless of the power of the lens. The lightening of the lens by the glasses of this invention is about 6.5-7%.

Summary of the Invention

5 The glasses of the invention belong to the base system $\text{SiO}_2\text{-B}_2\text{O}_3\text{-TiO}_2\text{-R}_2\text{O}$ ($\text{R} = \text{Li, Na, K}$) and are prepared from a batch composition consisting essentially, in weight percent on the oxide basis:

	SiO_2	49-71	$\text{Li}_2\text{O} + \text{Na}_2\text{O} + \text{K}_2\text{O}$	8-20
10	B_2O_3	5-26	TiO_2	1.8-6
	Al_2O_3	0-14	ZrO_2	0-5.5
	Li_2O	0-4	As_2O_3 and/or Sb_2O_3	0-0.7
	Na_2O	0-16	Cl and/or Br	0-1
	K_2O	0-20	CaO and/or MgO	
15			and/or ZnO and/or BaO	0-4

The content of SiO_2 lies between about 49-71% approximately and results from the choice of the other glass components whose content limitations are described below.

20 B_2O_3 is an essential element of the glass because it especially makes it possible to obtain a low density; when B_2O_3 increases, the density of the glass decreases, the UV cutoff rises and the viscosity of the glass at high temperature decreases, which facilitates
25 its melting and forming. To eliminate B_2O_3 from the glass would lead, on the one hand, to a density situated at the higher admissible limit, and, on the other hand, to higher melting and forming temperatures. Therefore, the glass will contain at least 5%. Above
30 26%, the SiO_2 content would have to be greatly reduced,

thereby reducing the chemical resistance of the glass and the transmission.

The presence of Al_2O_3 is not indispensable; nevertheless, the most preferred glasses will contain some. As a matter of fact, besides improving the chemical resistance, Al_2O_3 substituted for SiO_2 reduces the density and, more significantly, increases the UV cutoff. Above about 14%, the solubility of TiO_2 in the glass is greatly diminished and, in a high content, it precipitates during the course of cooling. If one seeks to obtain glasses having a UV cutoff higher or equal to 325nm, it is indispensable that the Al_2O_3 content be greater than 2-3%, if B_2O_3 is less than about 14%.

TiO_2 is the determining element for the UV cutoff. Therefore, a minimum amount of 1.8% is necessary to obtain a UV cutoff on the order of 310nm. To attain 325nm, TiO_2 should be greater than approximately 4% with the previously-stated condition with respect to Al_2O_3 and B_2O_3 . Above 6% TiO_2 , the tendency to opacify during the course of cooling is increased and that particularly in the glasses containing a low content of alkali metal oxides (the latter is necessary in order not to exceed the desired index value). Besides its indispensable presence for UV absorption, TiO_2 contributes to the refractive index. Depending upon the content thereof, the index is adjusted with the alkali metal oxides, the concentration of ZrO_2 , and/or of the alkaline earth metal oxides and/or ZnO .

ZrO_2 is preferred over MgO , CaO , BaO , or ZnO for adjusting the index when the alkali metal oxides do not suffice.

0151346

With respect to the alkali metal oxides, the sum $\text{Li}_2\text{O} + \text{Na}_2\text{O} + \text{K}_2\text{O}$ will range between about 8-20%. Below 8%, the viscosity of the glass is high and the transmission decreases. On the other hand, the solubility of TiO_2 in the glass decreases which promotes opacification. To avoid phase separation of the matrix, the presence of Al_2O_3 is recommended when the content of alkali metals is close to the minimum level. The maximum concentration of alkali metal oxides is determined principally by the density, the refractive index, and the chemical durability. The proportion of the alkali metal oxides is adjusted as a function of the amount of TiO_2 , B_2O_3 , and Al_2O_3 in order to obtain the best compromise of properties - facility of melting and forming. If utilized alone, Na_2O and K_2O will be limited to about 16% and 20%, respectively. Li_2O will not exceed 4% because the tendency of the glass to opalize increases (linked to the insolubility of TiO_2). In particular, when TiO_2 is greater than 4% in the presence of average amounts of Al_2O_3 and B_2O_3 , the concentration of Li_2O will be maintained below 3%. Based upon weight percentages and in substitution with regard to SiO_2 , the contribution to the index and to the density increases in the following order: K_2O , Na_2O , Li_2O . In general, the UV cutoff diminishes when the quantity of alkali metal oxides increases. Therefore, to obtain a high cutoff (>325nm), the total content will preferably be less than about 15%.

When TiO_2 is greater than 3-3.5%, the glass is found to be more sensitive to the melting conditions in the sense that a coloration ("rose-orange") unacceptable to a glass called "white" can be observed

in certain cases. This is probably linked to the presence of Ti^{+3} ions; reducing melting conditions will be avoided. To improve the stability with respect to variations in melting conditions or batch materials, and in order to obtain a "white" glass regardless of the TiO_2 content and particularly at 5% TiO_2 , which leads to a high UV cutoff, As_2O_3 and/or Sb_2O_3 will be added. A maximum quantity of 0.7% will be employed. As_2O_3 is preferred to Sb_2O_3 .

As_2O_3 and Sb_2O_3 contribute equally to the fining of the glass. In certain cases, those fining agents are not sufficient and chlorine (with or without bromine) will be introduced into the batch materials in the form of chlorine (bromine) compounds such as chloride (bromide) of sodium or potassium. In view of the volatilization during the melting process, only a fraction of the batched quantity will be present in the final glass.

Prior Art

United States Patent No. 2,454,607 discloses glasses designed for sealing to a nickel-iron alloy, the glasses having compositions consisting, in weight percent on the oxide basis, of

	B_2O_3	20-24	Na_2O	≥ 2
	Al_2O_3	3-6	K_2O	≥ 2
	TiO_2	2-5	Li_2O	7-12
	ZrO_2	0.5-1.5	SiO_2	56-68

No mention is made of ophthalmic applications, of a high UV cutoff, or of a colorless glass. Moreover, the Li_2O content is much higher than can be tolerated in the subject invention.

United States Patent No. 4,224,074 describes glass frits suitable for decorating glass, glass-ceramic, and ceramic articles, the frits consisting essentially, in weight percent on the oxide basis, of

5	SiO_2	29-55	Na_2O	4-20
	B_2O_3	7-31	Li_2O	0-7
	Al_2O_3	2-8	$\text{Na}_2\text{O} + \text{Li}_2\text{O}$	6-24
	ZrO_2	5-16	F	0.75-4

No mention is made of ophthalmic applications, of a high UV cutoff, or of a colorless glass. Moreover, fluoride is a required component, which element forms no part of the subject invention, and TiO_2 is merely an optional ingredient.

Description of Preferred Embodiments

15 The invention is illustrated through the examples provided in the attached table. The compositions are given in batched weight percentages. The batch materials utilized (and notably the source of SiO_2) must be carefully selected in order to obtain a minimum amount of Fe_2O_3 . As a matter of fact, Fe_2O_3 in too large a quantity (greater than about 100 PPM in the glass) leads to a yellow coloration. This coloration results from the known interaction between Fe_2O_3 and TiO_2 . Particularly for SiO_2 , one utilizes quartz wherein the Fe_2O_3 content is on the average less than 10 PPM. The other principal batch materials that can be utilized are boric acid $[\text{B}(\text{OH})_3]$, boric anhydride, the carbonates of Li_2O , Na_2O , and K_2O , titanium oxide, zirconium oxide, or zircon.

30 In the presence or not of As_2O_3 , at least 2% Na_2O or K_2O will be introduced in the form of nitrates in

order to obtain oxidizing conditions during melting of the mixture of batch materials.

5 The examples of the invention were prepared from mixtures representing 100 grams to several kilograms of glass. Melting of the batch materials took place at 1250°-1350°C following which the temperature was raised to 1400°-1460°C for homogenizing and fining the glass. Pouring took place after cooling to a temperature allowing either the forming of a bar or the pressing of
10 a disc. The corresponding viscosity ranged between 100-1000 poises. The total time of the operation was on the order of 3-7 hours. After forming, the glass was annealed at about 480°C with a cooling rate to ambient temperature of 60°C/hour; the properties were
15 then determined.

Measurements of refractive index and Abbe number were carried out according to conventional methods (for n_d the yellow ray of He was used) on glasses having been cooled from 480°C to ambient temperature at the
20 rate of 60°C/hour. Density was measured by the immersion method and expressed in g/cm^3 .

The chemical resistance in acid medium was evaluated by the A.O. test described in the journal Applied Optics, 7, No. 5, page 847, May, 1968. It
25 consists of determining the loss of weight of a polished sample immersed at 25°C for 10 minutes in a 10% by weight aqueous solution of HCl. The loss of weight is expressed in mg/cm^2 .

The transmission curve was recorded at a thickness
30 of 2mm with the aid of a Hewlett-Packard spectrophotometer (type 8450A).

The glasses of the invention can be tinted for an ophthalmic application by using conventional colorants:

transition metal oxides or rare earth oxides or other known colorant elements. The total content of these colorants will not generally exceed 2%.

The glasses of the invention can be strengthened according to current techniques of thermal or chemical tempering. In the latter case, the strengthening requires the replacement of a Na^+ and/or Li^+ ion in the glass by Na^+ and K^+ ions in a bath of molten nitrates, which implies that the glass does not contain K_2O as the only alkali metal oxide.

Preferably, and in order to obtain a UV cutoff higher than about 325nm, the glasses will be prepared from a batch composition consisting essentially, in weight percent on the oxide basis:

15	SiO_2	54-70	$\text{Li}_2\text{O} + \text{Na}_2\text{O} + \text{K}_2\text{O}$	10-13
	B_2O_3	9-22	TiO_2	4-6
	Al_2O_3	3-10	ZrO_2	0-2
	Li_2O	0.5-3	As_2O_3	0.10-0.50
	Na_2O	3-9	Cl	0.2-0.7
20	K_2O	3-10		

As previously described, the TiO_2 content must be adjusted as a function of the Al_2O_3 , B_2O_3 , and alkali metal oxide contents in order to obtain a UV cutoff greater or equal to 325nm (see table of examples). For example, a low content of Al_2O_3 and B_2O_3 must be associated with a high concentration of TiO_2 .

The particularly preferred glasses, because of their excellent properties and their facility for melting and forming on an industrial scale, are

prepared from a batch composition consisting essentially, in weight percent on the oxide basis:

	SiO ₂	56-62	Li ₂ O + Na ₂ O + K ₂ O	10.5-12.5
	B ₂ O ₃	15-20	TiO ₂	4.2-5.5
5	Al ₂ O ₃	4-7.5	ZrO ₂	0-1.5
	Li ₂ O	1-2.5	As ₂ O ₃	0.10-0.50
	Na ₂ O	3-7	Cl	0.2-0.7
	K ₂ O	3-6		

The most especially preferred glass is that of Example 1. This glass has a low density (2.37 g/cm³), a high UV cutoff (330nm), and exhibits no coloration in the visible. Furthermore, it has excellent chemical durability (loss of weight in the A.O. test = 0.004mg/cm²) and can be easily produced in a continuous melting unit. It can also be formed at a viscosity of 3000-6000 poises with no problem of devitrification.

Table

		<u>1</u>	<u>2</u>	<u>3</u>	<u>4</u>	<u>5</u>	<u>6</u>	<u>7</u>
	SiO ₂	58.89	55.91	69.21	69.21	59.26	65.69	58.89
	B ₂ O ₃	17.28	20.26	9.94	6.96	22.38	15.12	13.53
5	Al ₂ O ₃	6.19	6.19	3.21	6.19	1.23	2.21	9.94
	Li ₂ O	1.8	2.4	1.8	1.8	1.81	1.79	2.4
	Na ₂ O	4.09	4.09	4.09	4.09	6.11	4.07	4.09
	K ₂ O	5.81	5.81	5.81	5.81	3.84	5.79	5.81
	TiO ₂	5.07	4.47	5.07	5.07	4.5	4.46	4.47
10	Cl	0.57	0.57	0.57	0.57	0.57	0.57	0.57
	As ₂ O ₃	0.3	0.3	0.3	0.3	0.3	0.3	0.3
	n _d	1.5231	1.5213	1.5255	1.5231	1.5259	1.5226	1.5227
	V _d	53	54.7	54.1	53.7	55	55.3	53.94
	D	2.37	2.36	2.41	2.40	2.42	2.39	2.38
15	% Trans.							
	400nm	90.1	89.7	90.1	90.4	89.9	90.2	90
	UVnm							
	Cutoff	330	326	325	327	324	323	327

Table
- Continued -

		<u>8</u>	<u>9</u>	<u>10</u>	<u>11</u>	<u>12</u>	<u>13</u>	<u>14</u>
	SiO ₂	63.58	58.9	58.91	56.33	62.13	64.35	64.35
5	B ₂ O ₃	14.1	15.29	17.87	18.15	14.35	12.27	14.27
	Al ₂ O ₃	3.2	6.19	6.19	6.19	6.22	3.23	3.23
	Li ₂ O	-	2.79	1.8	1.8	0.81	1.81	1.81
	Na ₂ O	6.05	3.09	9.89	4.09	6.1	4.12	4.12
	K ₂ O	5.78	8.79	-	5.81	3.83	5.85	5.85
10	MgO	-	-	-	-	-	4	-
	CaO	-	-	-	-	-	-	2
	ZnO	1.98	-	-	-	-	-	-
	ZrO ₂	-	-	-	4.99	-	-	-
	TiO ₂	4.45	4.08	4.47	2.07	5.69	3.5	3.5
15	Cl	0.56	0.57	0.57	0.57	0.57	0.57	0.57
	As ₂ O ₃	0.3	0.3	0.3	-	0.3	0.3	0.3
	n _d	1.5191	1.5269	1.5266	1.5205	1.5212	1.5224	1.5241
	v _d	54.6	55.3	54.1	57.1	51.8	57.2	56.4
	D	2.40	2.41	2.40	2.39	2.37	2.41	2.41
20	% Trans.							
	400nm	91.2	90.6	90.7	90.7	89.5	89.4	91.8
	UVnm							
	Cutoff	323	322	324	311	333	319	320

Table
- Continued -

		<u>15</u>	<u>16</u>	<u>17</u>	<u>18</u>	<u>19</u>	<u>20</u>	<u>21</u>
	SiO ₂	64.35	58.89	57.43	57.19	62.89	56.68	51.08
5	B ₂ O ₃	14.27	10.55	18.15	18.07	16.16	17.87	18.18
	Al ₂ O ₃	3.23	12.92	6.19	6.17	3.21	6.19	6.21
	Li ₂ O	1.81	2.4	1.8	1.79	1.8	-	0.5
	Na ₂ O	4.12	4.09	4.09	5.06	4.09	13.92	-
	K ₂ O	5.85	5.81	5.81	5.78	5.81	-	18.68
10	ZnO	2	-	-	-	-	-	-
	ZrO ₂	-	-	2.98	2.97	1.99	-	-
	TiO ₂	3.5	4.47	2.98	2.97	3.48	4.47	4.48
	Cl	0.57	0.57	0.57	-	0.57	0.57	0.57
	As ₂ O ₃	0.3	0.3	-	-	-	0.3	0.3
15	n _d	1.5200	1.5228	1.5203	1.5250	1.5221	1.5230	1.5195
	v _d	55.8	53.7	55.8	56.8	56.5	54.1	54.3
	D	2.40	2.39	2.38	2.42	2.39	2.42	2.38
	% Trans.							
	400nm	90	90.5	91	91.1	89.8	89.9	90.4
20	UVnm							
	Cutoff	320	330	317	316	319	323	323

0151346

CLAIMS:

1. A glass for ophthalmic applications having a refractive index of 1.523 ± 0.004 , an Abbe number between 51-59, a density less than 2.43g/cm^3 , a transmission at 400nm in 2mm thickness greater than 89%, and a UV cutoff between 310-335nm, characterized in that it is prepared from a batch composition consisting essentially, in weight percent on the oxide basis, of:

10	SiO_2	49-71	$\text{Li}_2\text{O} + \text{Na}_2\text{O} + \text{K}_2\text{O}$	8-20
	B_2O_3	5-26	TiO_2	1.8-6
	Al_2O_3	0-14	ZrO_2	0-5.5
	Li_2O	0-4	As_2O_3 and/or Sb_2O_3	0-0.7
	Na_2O	0-16	Cl and/or Br	0-1
15	K_2O	0-20	CaO and/or MgO	
			and/or ZnO and/or BaO	0-4

2. A glass according to claim 1 having a UV cutoff higher than about 325nm characterized in that it is prepared from a batch composition consisting essentially, in weight percent on the oxide basis, of:

20	SiO_2	54-70	$\text{Li}_2\text{O} + \text{Na}_2\text{O} + \text{K}_2\text{O}$	10-13
	B_2O_3	9-22	TiO_2	4-6
	Al_2O_3	3-10	ZrO_2	0-2
	Li_2O	0.5-3	As_2O_3	0.10-0.50
25	Na_2O	3-9	Cl	0.2-0.7
	K_2O	3-10		

3. A glass according to claim 2 characterized in that it is prepared from a batch composition consisting

0151346

essentially, in weight percent on the oxide basis, of:

	SiO ₂	56-62	Li ₂ O + Na ₂ O + K ₂ O	10.5-12.5
	B ₂ O ₃	15-20	TiO ₂	4.2-5.5
	Al ₂ O ₃	4-7.5	ZrO ₂	0-1.5
5	Li ₂ O	1-2.5	As ₂ O ₃	0.10-0.50
	Na ₂ O	3-7	Cl	0.2-0.7
	K ₂ O	3-6		

4. A glass according to claim 3 characterized in that it is prepared from a batch composition consisting essentially, in weight percent on the oxide basis, of:

	SiO ₂	58.89	K ₂ O	5.81
	B ₂ O ₃	17.28	TiO ₂	5.07
	Al ₂ O ₃	6.19	As ₂ O ₃	0.3
	Li ₂ O	1.8	Cl	0.57
15	Na ₂ O	4.09		

~~5. A glass according to claim 1 characterized in that it is tinted by up to 2% by weight relative to the weight of the glass of at least one colorant element.~~



European Patent
Office

EUROPEAN SEARCH REPORT

0151346

EP 84 30 8760

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int. Cl. 4)
X	US-A-4 001 019 (T. YAMASHITA) * Examples; claim *	1-5	C 03 C 3/089 C 03 C 3/091 C 03 C 4/08
X	BE-A- 551 389 (PPG) * Page 6, table II; claim 1 *	1-5	
X	CHEMICAL ABSTRACTS, vol. 92, no. 4, 28th January 1980, no. 27323u, Columbus, Ohio, US; & JP - A - 79 113 618 (TOSHIBA KASEI KOGYO K.K.) 05-09-1979 * Abstract *	1	
X	GB-A-2 115 403 (CARL-ZEISS-STIFTUNG) * Examples 1-10 *	1	
			TECHNICAL FIELDS SEARCHED (Int. Cl. 4)
			C 03 C 3/00
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 20-03-1985	Examiner BOUTRUCHE J.P.E.
CATEGORY OF CITED DOCUMENTS			
X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document		T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document	

EPO Form 1503 03 82